

TEST REPORT



Report No.: A2002051-C01-R03

Date: March 06, 2020

Page 1 of 3

Applicant: Shenzhen Lezheng Technology Co., Ltd
Address: B building H block, North Industrial Park, LuoYan Street, Baoan District, Shenzhen City.

The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client:

Sample Name	Silicone mask
Lot No.	2020022401
Model No.	S8/S8Pro/S9
Manufacturer	Shenzhen Lezheng Technology Co., Ltd
Sample Received Date	February 26, 2020
Testing Period	February 26, 2020 – March 06, 2020
Test Method & Test Result	Please refer to following pages.

Test Requested

As specified by client, according to FDA 21CFR 177.2600 Rubber articles intended for repeated use to test Total extractives in distilled water at reflux temperature and Total extractives in N-hexane at reflux temperature in the submit sample(s)

Result

PASS

Tested by:

Lee Li

Approved by:

Anne Zhao

Reviewed by:

Tony Gmy

Date of issue: March 06, 2020



TEST REPORT



Report No.: A2002051-C01-R03

Date: March 06, 2020

Page 2 of 3

Tested Sample/Part Description

No.1: Milky silicon

Test method

Tested Item(s)	Test Method	Measured Equipment(s)
Total extractives	FDA 21CFR 177.2600	Analytical Balance

Test Result

1. Total extractive in distilled water at reflux temperature

Test Item(s)	Result	MDL	Limit	Unit
	No.1			
First 7 hours extraction	1.3	0.5	20	mg/in ²
Succeeding 2 hours extraction	N.D.	0.5	1	mg/in ²

2. Total extractive in n-hexane at reflux temperature

Test Item(s)	Result	MDL	Limit	Unit
	No.1			
First 7 hours extraction	11.5	0.5	175	mg/in ²
Succeeding 2 hours extraction	0.9	0.5	4	mg/in ²

Remark: N.D. = Not Detected (<MDL)
MDL = Method Detection Limit

TEST REPORT




Report No.: A2002051-C01-R03

Date: March 06, 2020

Page 3 of 3

Tested sample photo(s)

No.1



--- End of report ---

Statement:

1. The sample(s) and sample Information was/were provided by the client who should be responsible for the authenticity which ALPHA hasn't verified;
2. The result(s) shown in this report refer(s) only to the sample(s) tested;
3. Without written approval of ALPHA, this report can't be reproduced except in full.

Shenzhen Alpha Product Testing Co., Ltd.

Building i, No.2, Lixin Road, Fuyong Street, Bao'an District, 518103, Shenzhen, Guangdong, China